

-Specification

Iodine number	min. 800(mg/g)
Moisture content	max. 5%
Wettability	min. 95%
Hardness	85-95%

-Typical properties

Surface area	900 m ² /g
Methylene blue number	200 mg/g
Total pore volume	Max. 0.8 cm ³ /g
Water soluble ash	0.2%
Apparent density	200-300 kg/m ³
pH	8-8.5

Particle size: Granular and Powder